

DINITROL Penetrant LT

Durable cavity protection product with very broad spectrum of applications

DINITROL PENETRANT LT is a wax and resin based product with a very wide range of applications.

- » Petroleum resin-reinforced film
- » Improved wear resistance
- » Cavity and surface applications
- » Meets or exceeds MIL 16173 D/E Gr. 2 and 3





Equipment (not for spray can)

DINITROL Spray Tool HS 1-P Art. No. 1700700

DINITROL Spray Tool UBS/HR GSI Art. No. 1701900 **DINITROL Pump Unit for 20 L Pails** Art. No. 1705100

DINITROL Airless Pump 1:26 Art. No. 1705900

DINITROL Penetrant LT

Art. No.	Size	Package	Color
11470	500 ml	Can	Trans. beige
11080	1 L	Can	Trans. beige
11078	60 L	Drum	Trans. beige
11077	208 L	Drum	Trans. beige



DINOL U.S. Inc. 8500 Cotter Street, Lewis Center, OH 43035 Tel 740-548-1656, Fax 740-548-1657, www.dinol.com, info@dinolus.com

All data and recommendations are the result of careful tests by our laboratory. They only can be considered as recommendation which corresponds to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the misuse of our products. Therefore, a contractual legal relationship is not justified, and there are no secondary obligations arising from any purchase contracts.



DINITROL Penetrant LT

Technical Details

Product description

DINITROL Penetrant LT is a resin and wax based product that is suitable for cavity and general applications.

- Opaque to beige-transparent
- Excellent penetration
- Particularly water repellent
- Excellent low temperature properties
- Abrasion resistant

Applications

DINITROL Penetrant LT can be used for open surfaces and in cavities like doors and other parts on cars, trucks and busses. DINITROL Penetrant LT can also be used for parts that are stored for a longer time or transported under very corrosive conditions.

Method of use

DINITROL Penetrant LT is applied by spraying with manual or semi-automatic application equipment, and is suitable for either airmix or airless spraying. Stir the product before use. Application temperature should be between 15 and 30°C.

Pre-treatment Substrates

The surface to be treated must be free of loose corrosion.

Over-Coating / 2-Layer-Application

DINITROL Penetrant LT can be over-applied with any DINITROL bitumen underbody coating. For additional information, please consult DINOL GmbH.

Storage

DINITROL Penetrant LT should be stored at temperatures between + 15 ° C and + 30 ° C and protected from direct sunlight. The product stored dry, cool and in the original sealed packaging has a shelf life of 2 years.

Safety precautions

Additional information can be found in the safety data sheet.

Transportation

Additional information can be found in the safety data sheet.

Technical Data

Base	Resin and wax	
Colour	opal to beige transparent	
Density (DIN EN ISO 2811-1)*1	0,86 g/cm ³	
Viscosity at 23°C, DIN 4	18 seconds	
Solid content (DIN EN ISO 3251)*1	52% by weight	
Flash point	40°C	
Aromatic content in solvent	< 1%	
Recommended film thickness	40 µm	
Recommended film thickness wet	100 µm	
Drying time*1	2 hours	
Low temperature adhesion	- 40°C	
Effect on car paint	none	
Removability	White Spirit	
Heat resistance	> 110°C	
Salt spray test (DIN EN ISO 9227)	> 1000 h at 40 µm DFT	
Penetration 50 µm gap	> 30 mm	
Available in	500 ml Spray can, 1 L Miniservice, 60 L Drum, 208 L Drum	

Spray - Hazards identification 2.1. Classification of the substance or mixture GB CLP Regulation Aerosol 1; H222-H229; STOT SE 3; H336

Liter - Hazards identification 2.1. Classification of the substance or mixture GB CLP Regulation Flam. Liq. 3; H226; STOT SE 3; H336

For all relevant safety advices please read the material safety data sheet or the packaging label.

*1 Beim Raumtemperatur 20°C

All data and recommendations are the result of careful tests by our laboratory. They only can be considered as recommendation which corresponds to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the misuse of our products. Therefore, a contractual legal relationship is not justified, and there are no secondary obligations arising from any purchase contracts.